

А

## **Cement Test Certificate**

801 Berrimah Road, East Arm NT 0828 PO Box 39631, Winnellie NT 0821 T: +61 8 8984 0600 F: +61 8 8984 0610 www.adbri.com.au

## Final

Type LH Low Heat Cement

**Product Certified:** 

	rounder eer time u.	i jpe in i	on near cement	
-	Test Certificate Number:	170534		
I	Produced At:	Northern C	Cement, Darwin Plant, NT	
5	Sample Code:	B05db25		
:	Sample Date:	8/09/2017		
Nominal Blen	ıd		Requirements	Result
Clinker				30%
Ground Granulated Iron Blast-Furnace S	Slag			65%
Mineral Addition			Max 7.5 %	Nil
Calcium Sulphate				<5 %
Minor Additional Constituents			Max 5 %	Nil
Reportable Property			Requirements of	
		t Method	AS3972	Result
3 Day Strength		AS2350.11	N/R	18.6 MPa
7 Day Strength		AS2350.11	Min 10.0 MPa	30.5 MPa
28 Day Strength		AS2350.11	Min 30.0 MPa	54.8 Mpa
Initial Set Time		AS2350.4	Min 45 min	120 min
Final Set Time		AS2350.4	Max 600 min	240 min
Soundness		AS2350.5	Max 5 mm	0 mm
Sulfuric Anhydride content (SO3	3)	AS3583.8	Max 3.5 %	2.8 %
Chloride Ion		AS3583.13	Max 0.10 %	0.006 %
Peak Temp Rise		AS2350.7	Max 23 °C	22.0°C
Other Properties				
SiO <sub>2</sub>		AS2350.2	N/R	27.8 %
Al <sub>2</sub> O <sub>3</sub>		AS2350.2	N/R	9.8 %
Fe <sub>2</sub> O <sub>3</sub>		AS2350.2	N/R	1.7 %
CaO		AS2350.2	N/R	51.8 %

## These test results apply specifically to the above designated sample as received for the date shown.

Adelaide Brighton Cement Birkenhead Laboratory (Accredited number: 252), 62 Elder Rd Birkenhead 5015, is responsible for testing in accordance with AS2350.2:2006, AS2350.8:2006, AS3583.8:19991 and AS3583.13:1991.

AS2350.2

AS2350.2

AS2350.2

AS2350.8

AS2350.3

This document shall not be reproduced except in full.

Adelaide Brighton Cement Angaston Laboratory (Accredited number: 73), Stockwell Rd Angaston 5353, is responsible for testing in accordance with AS2350.3:2006, AS2350.4:2006, AS2350.5:2006, AS2350.7:2006, AS2350.11:2006 and AS2350.12:2006.

This despatch grab sample complies to the requirements of AS3972:2010, Type LH Cement.

N/R = No Requirement



MgO

Na<sub>2</sub>O Equivalent

Loss on Ignition

**Fineness Index** 

REMARKS

Normal Consistency

Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

**Approved Signatory** F. Pope

4.1 %

0.5 %

0.4 %

32.0 %

385 m²/kg

Issue Date: 17/10/2017

N/R

N/R

N/R

N/R

N/R